



FOR GOOD REASONS

---

pan**DOMO**<sup>®</sup> W3 2.0

**Decorative finishing render**

concrete  
grey

---

For creating and designing the surfaces of walls and ceilings  
in internal areas

Pre coloured

Cement/Polymer based

Hardens and dries rapidly to a stress-free layer without  
cracks in all thicknesses

Easy to apply

Excellent adhesion

High yield



---

Manufacturer  
with certified quality system  
as per DIN EN ISO 9001

ARDEX GmbH  
58430 Witten · P.O. Box 61 20  
GERMANY  
Telephone: +49 (0) 23 02/664-0  
Telefax: +49 (0) 23 02/664-437  
kundendienst@ardex.de  
www.ardex.de

## Decorative finishing render

---

### Use:

Installation of illustrative finishes characterised by a creative design, such as surfaces in exhibition rooms, foyers, public buildings, sales premises and in private residences.

### Description:

Grey powder made of special cement, flexible polymer additives and selected fillers.

The powder is mixed with water to give a supple mortar which can be applied as a finishing compound in both thin and thick layers and is workable approx. 30 minutes.

The hardened render is inert, virtually tension free and vapour permeable.

### Substrate preparation:

Suitable substrates

- concrete
- cement and lime plaster
- gypsum plaster and gypsum wall boards
- masonry
- gypsum plasterboards
- gypsum fibre boards
- tiles and stone slabs
- colourfast dispersion coatings
- old latex paints
- acrylic paints
- enamel coatings
- alkyd resin coatings
- glass fibre hangings, painted

Must be dry, solid, stable as well as free of dust, dirt and other barrier materials.

Remove old, weakly adhered residues or coatings, loose plaster/render and wall papers.

Acrylic enamel coatings, alkyd resin coatings as well as tiles and stone slabs have to be pre-filled with a thin layer of PANDOMO® W3 2.0 concrete grey.

For masonry and all surfaces with mixed backgrounds, apply a coat of PANDOMO® Primer, diluted 1:2 with water or ARDEX P 4 multipurpose primer undiluted, to avoid colour tone differences.

### Application:

Potable water is put into a clean mixing container and whilst stirring vigorously powder is mixed in to give a supple, lump-free mortar.

Approximately 2.5 l of water are needed to mix 5 kg of PANDOMO® W3 2.0 concrete grey powder.

After a maturing period of 1–3 minutes and repeated stirring, the mortar can be applied at temperatures between 18–20°C within approx. 30 minutes.

Small holes and minor, stable cracks can be filled using Pandomo® W3 2.0 concrete grey. When preparing two-dimensional areas with finishing render, the first preparation layer should be tinted to adapt to the required colour tone, up to a nominal layer thickness of 2 mm.

When trowelling the surface to produce decorative effects the minimum thickness should be 1 mm.

### PANDOMO® Wall 2.0 – Designing smooth wall and ceiling surfaces:

The follow-up treatment can start approx. 60 minutes after render application; at temperatures between 18 and 20°C. Time can vary depending on the temperatures on site. Use a moist sponge to dampen the surface, and venetian smoothing blade to finish the surface.

Having allowed the render to dry (about 5 hours), the surface must be polished with a suitable eccentric grinder (e.g. Rotex from Festo) using a grinding disc with an abrasive grain size of 120. As an alternative grinding pads of messrs. Mirka 180 grid Abranet and 4000 grid Abralon can be used. We recommend to carry out a simple impregnation (bringing about a colour intensification) using PANDOMO® SL stone oil – see technical leaflet.

### PANDOMO® Wall-Unique – Designing structured wall and ceiling surfaces:

PANDOMO® W3 2.0 concrete grey can be designed using normal structuring tools within the processing time (30 minutes).

After a suitable drying period the surface is also polished and impregnated with PANDOMO® SL Stone oil.

## Decorative finishing render

### Note:

It is strongly recommended to prepare the substrate thoroughly before beginning the creative wall design. In addition a sufficiently large trial area should be completed for approval by the client.

Creative wall designs in residential bathrooms and lavatories can be carried out with PANDOMO® W3 2.0 concrete grey. It is not recommended for use within range of direct splashing or run-ning water in the proximity of showers.

There is no problem to reapply PANDOMO® W3 2.0 concrete grey directly over impregnated PANDOMO® W3 2.0 concrete grey areas during subsequent renovation works.

Product contains cement. Causes an alkaline reaction requiring protection of the skin and the eyes. If product comes into contact with the skin and the eyes, thoroughly rinse with water. In case of contact with the eyes, seek medical help.

Once hardened, the material is inert and non-hazardous.

### Technical data

#### according to ARDEX quality standards:

<b>Mixing ratio:</b>	approx. 2.5 l water : 5 kg powder equivalent to approx. 1 vol. of water : 1.8 vol. of powder
<b>Bulk density:</b>	approx. 0.9 kg/l
<b>Weight of fresh mortar:</b>	approx. 1.4 kg/l
<b>Material requirement:</b>	approx. 1.0 kg – 1.5 kg per m <sup>2</sup> per designed surface on a plane substrate.
<b>Working time (+20°C):</b>	approx. 30 min.
<b>Compressive strength:</b>	after 1 day approx. 4.5 N/mm <sup>2</sup> after 7 days approx. 8.0 N/mm <sup>2</sup> after 28 days approx. 13.0 N/mm <sup>2</sup>
<b>Tensile bending strength:</b>	after 1 day approx. 1.5 N/mm <sup>2</sup> after 7 days approx. 3.0 N/mm <sup>2</sup> after 28 days approx. 5.0 N/mm <sup>2</sup>
<b>Emicode:</b>	EC1R Plus very low emission
<b>Water vapour diffusion coefficient <math>\mu</math> according to DIN 53122 (whole system):</b>	approx. 210
<b>GISCODE:</b>	ZP 1 = product contains cement, low chromate content
<b>Packaging:</b>	5 kg bags supplied in packs of 4
<b>Storage:</b>	can be stored for approx. 6 months in dry rooms

We assume the warranty for the perfect quality of our products. Our handling recommendations are based on trials and practical experience; they can, however, only be regarded as general advice without a quality warranty, as we have no influence on work site conditions and the execution of the work.  
Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations.